

Product
Summary

IBC - 1000L

#### **Applications**

Sinopec JUSTAR J600 5W-30 Engine Oil is suitable for use in:

PAIL - 18L

- Gasoline engines equipped with catalytic converters.
- Direct-injection gasoline engines with multi-valves and turbochargers, such as those in high-performance passenger cars, racing cars and coaches.

available in bulk

• Gasoline engines that require an API SN/ILSAC GF-5 quality oil.

DRUM - 200L

#### Features and benefits

1L/4L/5L

- High viscosity index, synthetic technology base oils provide improved oxidation control compared to conventional oils, minimising the formation of sludge and deposits and reducing oil thickening. This ensures the oil stays in grade for longer and extends both oil and engine life.
- Excellent antiwear performance protects against engine wear and prolongs engine service life.
- The advanced low-ash additive system provides effective protection from deposits in gasoline engines equipped with turbochargers and electrically controlled high-pressure pump nozzles, and ensures optimum engine power output.
- Strict control of certain elements in the oil formulation ensures excellent catalyst compatibility and extends the life of three-way catalytic converters.
- Excellent temperature/viscosity characteristics ensure the protection of engine parts operating at both high and low temperatures.
- Low oil evaporation loss, a feature of the synthetic base oil, leads to improved fuel economy and reduces oil consumption, exhaust emissions and engine wear.
- Good elastomer compatibility ensures longer gasket and seal life.



# Typical data

Sinopec JUSTAR J600 5W-30 Engine Oil		
SAE grade	5W-30	
Kinematic viscosity, ASTM D 445		
cSt @ 40℃	61.56	
cSt @ 100℃	10.37	
Viscosity index, ASTM D 2270	158	
Dynamic viscosity, CCS, ASTM D 5293 cP @ -30℃	5270	
High-temperature, high-shear viscosity (HTHS), ASTM D 4683 cP @ 150°C	2.96	
NOACK volatility, ASTM D 5800	8.4	
Sulfated ash, wt%, ASTM D 874	0.94	
Total base number, mg KOH/g, ASTM D 2896	8.5	
Pour point, °C, ASTM D 97	-43	
Flash point (COC), °C, ASTM D 92	230	
Density @ 15°C, kg/l, ASTM D 4052	0.843	

These data are given as an indication of typical values and not as exact specifications.

# Industry and OEM specifications

# Sinopec JUSTAR J600 5W-30 Engine Oil meets the performance requirements of the following industry specifications:

API Service Classification	Petrol/Gasoline: SN (Resource Conserving), SM, SL and earlier specifications	
ASTM	D4485-2010	
ILSAC	GF-5	

Sinopec JUSTAR J600 5W-30 Engine Oil meets the performance requirements of the following OEM specifications:		
Toyota	GF-5 5W-30	
Ford	WSS-M2C946-A	



## Accuracy of information

Data provided in this PDS is typical and subject to change as a result of continuing product research and development. The information given was correct at the time of printing. The typical values given are subject to variations in the testing procedures and the manufacturing process may also result in slight variations. Sinopec guarantees that its lubricants meet any industry and OEM specifications referred to on this data sheet.

Sinopec cannot be held responsible for any deterioration in the product due to incorrect storage or handling. Information on best practice is available from your local distributor.

## Product and environmental safety

This product should not cause any health problems when used in the applications suggested and when the guidance provided in the Material Safety Data Sheet (MSDS) is followed. Please consult the MSDS for more detailed advice on handling; MSDSs are available from your local distributor. Do not use the product in applications other than those suggested.

As with all products, please take care to avoid environmental contamination when disposing of this product. Used oil should be sent for reclamation/recycling or, if not possible, must be disposed of according to relevant government/authority regulations.

The SINOPEC trademark is registered and protected.

Issued: March 2017

© Sinopec 2017

Sinopec JUSTAR J600 5W-30 Engine Oil



The information contained herein is subject to change without notification due to continuing research & development therefore properties may be subject to slight variations.